



October 7, 2016

Legacy Safety & SECURITY
125 Stafford Place
New Orleans LA 70124
Attn: Robert Hausman

Dear Mr. Hausman:

In accordance with your instructions, Oregon Ballistic Laboratories conducted Ballistic Resistance (V_0) testing on one sample.

The sample was tested in accordance with NIJ-STD-0101.06 Level IV (abbreviated) (modified) in an indoor range with the muzzle of the test barrel mounted 50 feet away from the target and positioned to produce 0-degree obliquity impacts. Four infrared light screens, in conjunction with time-based frequency counters, were positioned such that projectile velocity was measured 8.25 feet from the target. Penetrations were determined by examination of a 5.5-inch clay block mounted behind the test sample. Results for all testing performed for this purpose are summarized in the following table.

Test Sample		Ballistic Threat				Results			
Model No.:	Weight (lbs)	Projectile	Shots	Velocity (fps)		Penetrations	BFD (mm)		Pass/Fail
				Min.	Max.		Min.	Max.	
LSS-IV	5.29	.30 cal M2AP	3	2886	2886	0	36.18	39.43	Pass

Samples will be maintained at Oregon Ballistic Laboratories for 30 days and then discarded, unless other instructions are received. If you have any further questions or concerns, please contact us.

Sincerely,

Brandon Bertsch
Oregon Ballistic Laboratories



This report must not be used to claim product certification, approval, or endorsement by NVLAP, NIST, or any agency of the federal government.